

# VaporPro<sup>™</sup>

## ASTM-CERTIFIED VAPOR BARRIER FILM & TAPE

VaporPro<sup>™</sup> ASTM-Certified Class A Vapor Barrier is a high-performance polyethylene film designed for use as a vapor retarder under concrete slabs. This film is manufactured in the United States of America using high quality prime, virgin resins. VaporPro is designed as a low permeance, high strength, and high puncture resistant film that meets and exceeds the ASTM E1745-17 requirements for a Class A vapor retarder.



- Available in 10mil & 15mil gauge
- High visibility, bright green color
- Made in the USA
- Permeance <0.1 perms
- Tensile strength > 45lb/in
- Puncture resistance > 2200g
- ASTM E1745 Class A Certified
- Lifetime Warranty



10-15 MIL



High Visibility Color



Made in the USA



Heavy-Duty  
Performance



ASTM-Certified

It's time to  
**redefine  
possible**

Contact  
vaporpro@revolutioncompany.com  
972.216.3331  
revolutioncompany.com

Item #	Description	Thickness	Roll Size	Weight (lbs.)	Case Qty.	Pallet Qty.
G1014210	Sheeting 14 x 210 Green 10mil USVB	10 mil	14' x 210'	14112	1	12 rolls/pallet
G1014105RES	Sheeting 14 x 105 Green 10mil USVB	10 mil	14' x 105'	70.56	1	24 rolls/pallet
G1514140	Sheeting 14 x 140 Green 15mil USVB	15 mil	14' x 140'	14112	1	12 rolls/pallet
G151470RES	Sheeting 14 x 70 Green 15mil USVB	15 mil	14' x 70'	70.56	1	24 rolls/pallet

Item #	Description	Thickness	Roll Size	Backing	Case Qty.	Pallet Qty.
W754180	Tape 4 x 180 White	7.5 mil	3.77" x 180'	PE Film	12 rolls/case	36 cases/pallet

# VaporPro™ Product Specifications

## TECHNICAL DATA

Properties	Test Method	10 Mil	15 Mil	ASTM E1745-17 Class A, B, C
Color		Green	Green	
Thickness		10 mil	15 mil	
Roll Dimensions Commercial Residential		14 ft x 210 ft 14 ft x 105 ft	14 ft x 140 ft 14 ft x 70 ft	
Surface Area Commercial Residential		2,940 ft <sup>2</sup> 1,470 ft <sup>2</sup>	1,960 ft <sup>2</sup> 980 ft <sup>2</sup>	
Roll Weight Commercial Residential		141 lbs 71 lbs	141 lbs 71 lbs	
Classification	ASTM E1745-17	Class A, B, & C	Class A, B, & C	Class A, B, or C
Puncture Resistance	ASTM D1709 Method B Drop Height 60 inches	2645 g	3055 g	Class A = 2200 g Class B = 1700 g Class C = 475 g
Tensile Strength	ASTM D882	55 lbf/in	82 lbf/in	Class A = 45 lbf/in Class B = 30 lbf/in Class C = 13.6 lbf/in
Permeance New Material After Conditioning	ASTM F1249, E154 Section 7 Section 8 after wetting, drying, soaking Section 11 after heat conditioning Section 12 after low temp conditioning Section 13 after soil organism exposure	0.00807 0.00347 0.00300 0.00392 0.00541	0.00464 0.00383 0.00349 0.00311 0.00412	Class A, B, & C 0.1 Perms Max

\*3rd party independently tested